

Bontec® SG 20/20 F

Polypropylene Woven Geotextiles

Technical data sheet

Product description

Polymer	Density	Melting Point	Construction
100% Polypropylene	0,91 kg/dm ³	165 °C	Tapes

Properties

Mechanical Properties	Standard	Performance	Tolerance
Tensile strength - MD	EN ISO 10319	20 kN/m	-2,6 kN/m
Tensile strength - CMD	EN ISO 10319	20 kN/m	-2,6 kN/m
Elongation at maximum load - MD	EN ISO 10319	28 %	+/-6,4 %
Elongation at maximum load - CMD	EN ISO 10319	28 %	+/-6,4 %
Static puncture resistance (CBR)	EN ISO 12236	2,4 kN	-0,24 kN
Dynamic perforation resistance (cone drop)	EN ISO 13433	16 mm	+4 mm

Hydraulic Properties	Standard	Performance	Tolerance
Water permeability normal to the plane (Vlh50)	EN ISO 11058	10 l/m ² s	-3 l/m ² s
-	-	-	-
Characteristic Opening Size (O90)	EN ISO 12956	250 µm	+/-75 µm

Physical Properties	Standard	Performance	Tolerance
Thickness under 2 kPa	EN ISO 9863-1	0,5 mm	+/-0,10 mm
Weight	EN ISO 9864	108 g/m ²	+/-10,8 g/m ²
Length (+/- 1%) x width (+/- 1%)		100 x 5,25 m	
Roll diameter (+/- 10%)		32 cm	

Durability	Standard	Performance	
Predicted minimal durability in years in natural soils with 4 < pH < 9 and soil temperatures < 25°C	EN ISO 13438 - A2	25	
Maximum allowed time between installation and covering of the geosynthetic	EN 12224	2 weeks	

The Quality Management System of Bonar has been approved to the ISO 9001 Quality Management System Standard. Certificates are available on request.



The information set forth in this data sheet reflects the best knowledge at the time of publication. The document is subject to change pursuant to new developments and findings. The same reservation applies to the properties of the products described. No liability is undertaken for results obtained by usage of the products and information.